

## BOMOPRINT BLANC FLEX

<b>Characterization</b>	Ready for printing, hot curing white paste on aqueous base; for highly covering white prints or pastel-colored prints on dark, <u>elastic</u> textile qualities
<b>Chemical Structure</b>	White pigmented, basic paste; compound of synthetic dispersions, thickener and additives, free from white spirit and phthalates
<b>Supplied Form</b>	White, highly viscous paste
<b>Ionic Character</b>	Anionic
<b>pH Value</b>	7.6 – 9.5
<b>Viscosity</b>	18,000 - 26,250 mPas (Brookfield RVT 20/6)
<b>Storage</b>	If stored properly in a cool place between + 5 °C and + 25 °C in closed original containers, the product will be stable for about 12 months. Protect from frost and excessive heat. Opened containers must be closed again tightly.

---

The above given values are product describing data. Please consult the 'delivery specification' for binding product specifications. Further data about product properties, toxicological, ecological data as well as data relevant to safety can be found in the safety data sheet.

## Properties

### Processing / Fixation

BOMOPRINT BLANC FLEX is ready for printing and is normally used directly as a covering white paste. For pastel-colored prints BOMOPRINT BLANC FLEX can be colored with pigments, e.g. COLORMATCH dyestuffs. When being mixed with other white pastes, BOMOPRINT BLANC FLEX increases the flexibility .

If very high demands are made on the fastness properties or if critical fabric qualities have to be printed, it is possible to add a fixing agent to the print pastes which, however, may possibly decrease the flexibility.

We recommend stirring up BOMOPRINT BLANC FLEX prior to use; color additions or combinations with adhesive dispersions are to be homogeneously blended with the basic paste by means of suitable stirring units.

The fixation of the prints is usually effected by means of dry heat in the range of 130 °C - 160 °C. For special demands with a reduced fixing temperature or reduced fixation time, BOMOPRINT FIX 104 W can be used as a special low temperature cross linking agent after preliminary trials .

## **Film Properties / Handle**

Despite its good covering properties BOMOPRINT BLANC FLEX results in very soft and flexible white print effects, especially on stretchable knits and elastic fabric qualities.

## **Printing Properties / Fastnesses / Further Properties**

BOMOPRINT BLANC FLEX can be well processed with common screen printing methods. The best possible covering properties and an excellent degree of whiteness are achieved by printing in the last position.

White prints with BOMOPRINT BLANC FLEX produce brilliant, well covering white effects with a very good fastness level and stand out for their high flexibility on elastic fabric qualities. The adhesive power is also excellent on many textile qualities which are hard to wet such as closely woven fabrics for leisure wear.

---

## **Application Procedure**

### **Application Fields**

BOMOPRINT BLANC FLEX is mainly used for covering white prints on dark, stretchable knits and flexible elastic materials. In screen printing on closely woven fabrics, e.g. leisure wear, BOMOPRINT BLANC FLEX mostly shows a very good wetting and adhesion to the fabric.

### **Recommendation for Use / Processing**

#### **Material Structure / Substrates**

BOMOPRINT BLANC FLEX can be applied on a multitude of nowadays common textile qualities, preferably on elastic textile qualities.

In order to achieve good printing effects with a high fastness level, the substrates have to be dry, clean and possibly free from auxiliary rests or preparation add-ons. We generally recommend checking the suitability of the materials in preliminary tests, especially in case of impregnated or heat-sensitive textiles or dyed qualities (e.g. thermal migration of disperse dyestuffs).

In most cases a reduction of the fixing temperature and a correspondingly prolonged fixing time can improve this situation; if necessary, the fixing temperature may be additionally decreased by means of a special low temperature cross linking fixing agent.

#### **Additives and Auxiliaries**

##### BOMOPRINT FIX 120 W

With the addition of 5 – 8 % TUBASSIST FIX 120 W at fixation temperatures of 120 – 150 °C a good wash fastness without formaldehyde impact can be achieved. The fixing agent ought to be only added immediately prior to processing. Blended print pastes must be used up within two working days. The fixing agent would otherwise react without increasing the paste viscosity and would no longer be effective.

### BOMOPRINT FIX 104 W

With the addition of 1 - 2 % TUBASSIST FIX 104 W a good wash fastness can already be achieved at drying temperatures of clearly below 120 °C. The fixing agent ought to be only added immediately prior to processing. Blended print pastes must be used up within half a working day (2 - 4 hours) since the addition of the fixing agent leads to a strong increase in the print paste viscosity.

### COLORMATCH Color Pigments

For the production of pastel-colored matt prints we recommend adding 0.1 – 5.0 % COLORMATCH pigments. Due to the high white pigmentation of BOMOPRINT BLANC FLEX it is not possible to produce brilliant and deep shades.

### BOMOPRINT RETARDER

2.0 – 5.0 % of this retarder may be added to reduce the drying speed in the printing screens and at the same time to improve the printing properties. High concentrations may slow down the drying and fixation process which may then have to be adjusted.

#### **Diluting / Thickening**

In general not necessary; if need be, the viscosity can be lowered by adding some water (up to 10 %). The viscosity can be increased by homogeneously stirring in 0.1 - 0.5 % TUBIVIS DL 650.

#### **Cleaning of Working Utensils**

Immediately with cold water. On prolonged stoppages during printing the screens must be kept moist or cleaned intermediately. Slightly dried-in paste rests or color tinting on the screen lacquer can be softened with a suitable household detergent (e.g. dishwashing soap); cured paste rests can only be removed mechanically. We recommend checking the stability of the screen layers to the detergents in use with preliminary trials.

#### **Printing Process**

Application by means of all common screen printing methods with polyester monofilament screens of 26 - 55 threads/cm, preferably 30 - 40 threads/cm, depending on the design and the fabric quality.

The best possible covering power and highest whiteness degree are achieved by printing in the last position.

#### **Drying / Fixation**

May be carried out in one or in separate steps. For achieving maximum fastness properties the print pastes need to be cured by means of a heat treatment.

Water steam arising at the drying and fixation stage must be drawn off continuously by adequate ventilation. By doing so an insufficient fixation of the print pastes due to humidity accumulation in the drying and fixing zone is avoided.

Recommended conditions for drying + hot air fixation

	in the drying chamber	in the continuous drier
One step	130 - 150 °C, 20 - 5 min	140 - 160 °C, 6 - 3 min
Two step	Drying 80 - 120 °C, 10 - 5 min, possibly room temperature drying after pre-trials	
	Fixation 130 - 160 °C, 10 - 3 min	

When fixing with radiant heat or other sources of energy, it is essential to run meaningful trials prior to going into production.

### **Recommendation for Use**

Before going into production we urgently recommend carrying out pre-trials in order to test the suitability of the print pastes for the substrates to be used with regard to wetting, adhesion, fastness properties, heat stability and processing parameters and controlling everything as well during the production run.

**We reserve the right to modify the product and technical leaflet.**

**Our department for applied technique is always at your service for further information and advice.**

Our technical advice and recommendations given verbally, in writing or by trials are believed to be correct. They are neither binding with regard to possible rights of third parties nor do they exempt you from your task of examining the suitability of our products for the intended use. We cannot accept any responsibility for application and processing methods which are beyond our control.

**Edition: April 2014**

**Borchert + Moller GmbH & Co.KG**

**Kreuzäckerstr. 11-13, 72401 Haigerloch, Germany**

**Telephone: 07474/9565-0, Fax: 07474/9565-35**

**Email: [info@borchert-moller.de](mailto:info@borchert-moller.de), Homepage: [www.borchert-moller.de](http://www.borchert-moller.de)**