

TECHNICAL DATA SHEET

WS-1050-12



GLASS DECORATION sandblast effect

| Item | Description | Specification |
|-----------------|---|---|
| Front Layer PVC | Article Codes | WS-1050-12 |
| | Туре | SAV - Monomeric PVC Film |
| | Thickness | 100 my (± 10%) |
| | Front Colour | Translucent |
| | Back Colour | Translucent |
| | Surface Finish | Sandblast effect |
| | Shrinkage | ≥ 1,2 % |
| | Surface Tension | ≥ 30 % dn/cm |
| | Opacity | 28% |
| | 1 | |
| Adhesive | Туре | Clear solvent removable pressure sensitive glue |
| | Glue Thickness | 45 my |
| | Adhesion Temperature (Mounting) | 15 ÷ 35 °C |
| | Adhesive Strength | 0,95 Kg / inch (± 0,02) |
| | Release Force | 0,0059 Kg / inch (± 0,0005) |
| | Initial Adhesion-Ball Tack | ≥ 9 Steel Ball (GB4852-84/CNS) |
| | Holding Power | ≥ 2900 min. (GB4854-84/CNS) |
| Liner | Туре | White PE coated kraft paper |
| | Colour | White with green gride |
| | Weight | 118 gsm (105 my) |
| | Die Cutting | Suitable for plotter |
| | | |
| Applications | Indoor applications, glass decoration, plottering for graphics and light boxes advertising. Outdoor applications: suitable for max. 12/18 months. | |
| Printability | Suitable for Digital and Silk Screen printing. Suitable for solvent, eco-solvent and UV digital printers . All tests are made with the original printer manufacturer's inks on the following equipments: Roland, Mimaki, Scitex, Mutoh and HP. Notes: due to the wide number of ink producers and Digital Printing machines, weather conditions and printing variability, testing before printing is recommended. | |
| Storage Period | 12 months under ordinary condition at the temperature mean of 22 °C (min. 12 °C, max. 32 °C) and relative humidity of 45 - 65%. | |
| Safety Caution | RoHS - The multylayer composite film is in accordance with RoHS directive 2002/95/EC and its amendment directives. | |
| | EN71 - The multylayer composite film is in accordance with the European Standard on Safety of Toys EN71 Part 3 and with the Amercian Society for Testing and Materials - ASTM F963-07. | |
| | REACH - For the multylayer composite film, regarding REACH Regulation, we inform that the substance DEHP is present in a concentration of 18%. For further information, please refer to the certified copy available of the analyses worked out on the substances taken into consideration by REACH (Registration Evaluation Authorization of CHemicals), Complying with the Italian Decree-Law nbr. 133 issued on 14.09.2009 published on the Italian Gazzetta Ufficiale. | |
| Notes | Published information is based upon research and information which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of the products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages. All specifications are subject to changes without prior notice. | |

Update: September 2012